

Nepshaw Lane South, Morley, Leeds, LS27 7JQ Materials Testing Manager: D. J. Brockbank t: 0113 393 9791 e: dale.brockbank@wyjs.org.uk www.wyjs.org.uk/materialstesting



TEST REPORT

Client:	Steven Hargreaves Textile Group Ltd Overbrook House 14 Brookes Lane Whalley Lancashire BB7 9RG
Entry No:	78382
Date received:	11/08/2016
Client's Description:	Sample of fabric: Egyptian Cotton Natural Crib 7 Mattress Ticking, Colour: Cream, Twill Weave, 100% Cotton
Test Required:	Flammability BS 7175 ignition sources 0, 1 & 7
Pre-treatment:	Water soaking in accordance with BS5852:2006 Annex E followed by Line drying
Conditioning:	A minimum of 72 hours at indoor ambient and then 24 hours at 65+/-5% Relative Humidity, 20+/-5° C
Date Tests Completed:	30/08/2016
Method of Test:	BS 7175: 1989 (1994) Section 3

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Ignition Source	Positions	Observations	Result
0 (cigarette)	On top	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
1 (butane flame)	(i) On top (ii) Below Overhang	No flaming or progressive smouldering was observed after removal of the butane flame.	PASS
7 (wood crib)	(i) On Top (ii) Below overhang	Flaming ceased within the specified thirteen minute period after ignition of the crib and no progressive smouldering occurred.	PASS

-----End of Document------

This is hereby certified to be a correct return of the tests made of the items referred to herein

Dale Brockbank Materials Testing Manager 30 August 2016

- Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.
- Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 Uncertainty budgets for test methods contained within this report are available on request.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.



