

Nepshaw Lane South, Morley, Leeds, LS27 7JQ Materials Testing Manager: D. J. Brockbank

t: 0113 393 9791

e: dale.brockbank@wyjs.org.uk www.wyjs.org.uk/materialstesting



TEST REPORT

Client: Steven Hargreaves Textile Group Ltd

> Overbrook House 14 Brookes Lane

Whalley Lancashire BB7 9RG

73829 **Entry No:**

Date received: 18/02/2016

Client's Description: Sample of fabric: Marlow Stripe Mattress Ticking, Colour Black / Red/ Cream, Twill

Weave, 100% Cotton

Test Required: Flammability BS 7175 ignition sources 0, 1 (on top) & 5

Pre-treatment: None

Conditioning: A minimum of 72 hours at indoor ambient and then 24 hours at 65+/-5% Relative

Humidity, 20+/-5°C

Date Tests Completed: 25/02/2016

Method of Test: BS 7175: 1989 (2013) Section 3

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test: they are not intended as a means of assessing the full potential fire hazard of the bedcovers in use.

Ignition Source	Positions	Observations	Result
0 (cigarette)	On top	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
1 (butane flame)	On top	Flaming ceased within the specified two minute period after removal of the butane and no progressive smouldering occurred.	PASS
5 (wood crib)	(i) On top (ii) Below Overhang	Flaming ceased within the specified ten minute period after ignition of the crib and no progressive smouldering occurred.	PASS

This is hereby certified to be a correct return of the tests made of the items referred to herein

Giles Dive Senior Technician 25 February 2016

Unless instructed otherwise by the client sample remnants will be disposed of after 28 days.

Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.

Uncertainty budgets for test methods contained within this report are available on request.

This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.





